

# Latex-HR

Natural rubber, HR grade

Ideally suited to moulding applications

## Features

- Heat resistant sheet, formulated to retain strength and elasticity at temperatures up to 140°C/284°F.
- For bonding details, please contact us.
- Used as a vacuum diaphragm for composite moulding and for bonding laminates, where heat or autoclave pressure is necessary.

## Properties

	140°C	284°F
Maximum use temperature		
Colour	Dark grey	
Tensile strength	250m <sup>2</sup> /kg	135.6yd <sup>2</sup> /lb
Hardness (Shore A)	50	
Elongation at break	750%	

## Availability

Thickness	0.38-1.5mm	0.015-0.06in
Width	Up to 4m	Up to 4.37yd

## Storage

Store below 26°C/79°F and away from heaters.

Avoid damp storage conditions.

Protect from prolonged exposure to light, in particular bright sunlight and strong UV light, which will degrade sheeting.

Avoid contact with copper and copper containing alloys, which may stain the sheeting.

Avoid contact with oils, solvents and greases, which will destroy natural rubber.

## Health & safety

Handling of these products must conform to individual company guidelines and health and safety regulations.

All statements, technical information and recommendations contained in this data sheet are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any subsequent contract. All products are sold subject to the Cytec's Standard Terms and conditions of Sale. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. It is the responsibility of those wishing to sell items made from or embodying the products to inform the user of the properties of the products and the purposes for which they may be suitable, together with all precautionary measures required in handling those products. The information contained herein is under constant review and liable to be modified from time to time.

© Copyright 2012 – Cytec Process Materials (Keighley) Ltd, Cytec Process Materials (CA) Inc, Cytec Process Materials (Toulouse) Sarl, Cytec Process Materials (Milan) Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.